

Heraform® R900 NAT

Acetal (POM) Copolymer

Radici Plastics

Message:

POM Acetal copolymer. Standard grade for injection moulding of details with high mechanical requirement. Natural colour
ISO 1043 : POM

General Information			
Features	Copolymer		
UL File Number	E116324		
Appearance	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	POM		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	8.00	cm ³ /10min	ISO 1133
Water Absorption (Saturation, 23°C, 2.00 mm)	0.70	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2850	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	64.0	MPa	ISO 527-2/1A/50
Nominal Tensile Strain at Break	> 30	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.5	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	104	°C	ISO 75-2/Af
Vicat Softening Temperature	150	°C	ISO 306/B50
Melting Temperature ¹	166	°C	ISO 11357
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 50	mm/min	FMVSS 302
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Suggested Max Moisture	0.20	%	
Processing (Melt) Temp	200 to 220	°C	
Mold Temperature	80.0 to 100	°C	
Injection Rate	Moderate		
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

