

# McCann PP M20THPP12

Polypropylene Homopolymer

McCann Plastics Inc.

## Message:

McCann PP M20THPP12 is a Polypropylene Homopolymer (PP Homopolymer) product filled with 20% talc. It is available in North America. Applications of McCann PP M20THPP12 include automotive, household applications and industrial applications.

Characteristics include:

Flame Rated

Good Stiffness

Good UV Resistance

Homopolymer

UV Stabilized

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Additive	UV Stabilizer		
Features	General Purpose Good Flow Good Stiffness Good UV Resistance Homopolymer		
Uses	Automotive Applications General Purpose Industrial Applications Lawn and Garden Equipment		
Appearance	Black Colors Available Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.3 to 1.7	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	93		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	28.3	MPa	ASTM D638
Tensile Elongation (Yield)	8.0	%	ASTM D638
Flexural Modulus - Tangent	2830	MPa	ASTM D790

Flexural Strength	42.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	35	J/m	ASTM D256
Gardner Impact	0.904	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	127	°C	
1.8 MPa, Unannealed	70.6	°C	
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

