

PENTALLOY BS 8 GK30 H natural

Acrylonitrile Butadiene Styrene + PA

PENTAC Polymer GmbH

Message:

PA-ABS alloy, 30% glass bead reinforced, heat stabilised

General Information				
Filler / Reinforcement	Glass beads, 30% filler by weight			
Additive	heat stabilizer			
Features	Thermal Stability			
Agency Ratings	EC 1907/2006 (REACH)			
Appearance	Natural color			
Forms	Particle			
Processing Method	Injection molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.33	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Transverse flow	0.60	--	%	ISO 294-4
Flow	0.60	--	%	ISO 294-4
Water Absorption				ISO 62
Saturated, 23°C	3.8	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.7	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	4150	2300	MPa	ISO 527-2/1
Tensile Stress (Break)	65.0	60.0	MPa	ISO 527-2/5
Tensile Strain (Break)	10	> 25	%	ISO 527-2/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	8.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break	No Break		ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	170	--	°C	ISO 75-2/B
1.8 MPa, not annealed	70.0	--	°C	ISO 75-2/A
Melting Temperature	222	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Dielectric Strength	32	--	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	3.50	--		IEC 60250

Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.6 mm	HB	--		UL 94
3.2 mm	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	75		°C	
Drying Time	3.0		hr	
Suggested Max Moisture	0.050 - 0.13		%	
Suggested Max Regrind	20		%	
Rear Temperature	250 - 270		°C	
Middle Temperature	255 - 280		°C	
Front Temperature	260 - 270		°C	
Processing (Melt) Temp	245 - 285		°C	
Mold Temperature	60 - 100		°C	
Injection Pressure	65.0		MPa	
Screw L/D Ratio	18.0:1.0 to 22.0:1.0			
Screw Compression Ratio	2.2:1.0 to 2.8:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

