

Stanyl® TE250F6

Polyamide 46
DSM Engineering Plastics

Message:

Stanyl® TE250F6 is a Polyamide 46 (Nylon 46) material filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America. Important attributes of Stanyl® TE250F6 are:
Flame Rated
Flame Retardant
Heat Stabilizer
Typical application of Stanyl® TE250F6: Automotive

General Information				
UL YellowCard		E43392-235032	E47960-240064	E172082-225869
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Flame Retardant		
		Heat Stabilizer		
Features		Flame Retardant		
		Heat Stabilized		
Forms		Pellets		
Multi-Point Data		Isochronous Stress vs. Strain (ISO 11403-1)		
		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
		Shear Modulus vs. Temperature (ISO 11403-1)		
		Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.68	--	g/cm³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.1	--	%	
Flow	0.40	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.6	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2
--	12000	8000	MPa	
120°C	7500	--	MPa	
160°C	6200	--	MPa	
Tensile Stress				ISO 527-2
Break	180	125	MPa	
Break, 120°C	105	--	MPa	

Break, 160°C	95.0	--	MPa	
Tensile Strain				ISO 527-2
Break	2.5	3.5	%	
Break, 120°C	4.0	--	%	
Break, 160°C	4.0	--	%	
Flexural Modulus				ISO 178
--	11000	7300	MPa	
120°C	6500	--	MPa	
160°C	5000	--	MPa	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	10	kJ/m ²	
23°C	11	11	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	50	50	kJ/m ²	
23°C	60	60	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
-40°C	11	11	kJ/m ²	
23°C	11	11	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	290	--	°C	ISO 75-2/A
Melting Temperature ¹	295	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	2.5E-5	--	cm/cm/°C	
Transverse	5.5E-5	--	cm/cm/°C	
Thermal Index - 5000 hrs	163	--	°C	IEC 60216
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+10	ohms·cm	IEC 60093
Electric Strength	30	20	kV/mm	IEC 60243-1
Comparative Tracking Index	225	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.350 mm	V-0	--		
1.50 mm	V-0	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	280 to 320		°C	

Middle Temperature	300 to 320	°C
Front Temperature	300 to 320	°C
Nozzle Temperature	300 to 320	°C
Processing (Melt) Temp	305 to 320	°C
Mold Temperature	80.0 to 120	°C
Injection Rate	Moderate-Fast	
Back Pressure	2.00 to 10.0	MPa
Screw Compression Ratio	2.5:1.0	

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

