

OmniCarb™ PC/PBT 400

Polycarbonate + PBT

OMNI Plastics, LLC

Message:

OmniCarb™ PC/PBT 400 is a Polycarbonate + PBT (PC+PBT) product. It can be processed by injection molding and is available in North America. Primary characteristic: flame rated.

General Information			
Features	General Purpose		
Uses	General Purpose		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/5.0 kg)	23	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	55.0	MPa	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	2210	MPa	ASTM D790
Flexural Strength (Break)	83.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	530	J/m	ASTM D256
Flammability	Nominal Value	Test Method	
Flame Rating (3.18 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	104	°C	
Drying Time	3.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	249 to 271	°C	
Middle Temperature	249 to 277	°C	
Front Temperature	249 to 277	°C	
Nozzle Temperature	249 to 277	°C	
Processing (Melt) Temp	249 to 271	°C	
Mold Temperature	26.7 to 82.2	°C	
Back Pressure	0.345 to 0.689	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

