

TEDUR® R 9519

Polyphenylene Sulfide

ALBIS PLASTIC GmbH

Message:

TEDUR® R 9519 is a Polyphenylene Sulfide (PPS) product filled with 45% glass fiber. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America.

Characteristics include:

Flame Rated

Eco-Friendly/Green

REACH Compliant

RoHS Compliant

General Information			
Filler / Reinforcement	Glass Fiber,45% Filler by Weight		
Recycled Content	Yes		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.70	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	16000	MPa	ISO 527-2
Tensile Stress (Break)	155	MPa	ISO 527-2
Tensile Strain (Break)	1.5	%	ISO 527-2
Flexural Modulus	14000	MPa	ISO 178
Flexural Stress	240	MPa	ISO 178
Flexural Strain at Flexural Strength	1.8	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
--	6.0	kJ/m ²	
-30°C	6.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
--	30	kJ/m ²	
-30°C	30	kJ/m ²	
Unnotched Izod Impact Strength	30	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	260	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94

0.750 mm	V-0		
1.50 mm	V-0		
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	130 to 140	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	320 to 340	°C	
Mold Temperature	> 140	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

