

AKROMID® B3 GM 15/15 natural (3079)

Polyamide 6
AKRO-PLASTIC GmbH

Message:

AKROMID® B3 GM 15/15 natural (3079) is a 15% glass fibre and 15% glass bead reinforced polyamide 6 with good surface, low warpage and light inherent color
Applications are handles and switches in the automotive and electro industry.

General Information			
Filler / Reinforcement	Glass Bead,15% Filler by Weight		
	Glass Fiber,15% Filler by Weight		
Features	Good Surface Finish		
	Low Warpage		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
	Handles		
	Switches		
Appearance	Natural Color		
Resin ID (ISO 1043)	PA6 GF15 + GB15		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.34	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	1.1	%	
Flow	0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7200	MPa	ISO 527-2/1
Tensile Stress (Break)	130	MPa	ISO 527-2/5
Tensile Strain (Break)	3.5	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	64	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	221	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
Melting Temperature ¹	222	°C	DIN EN 11357-1
Flammability	Nominal Value	Unit	Test Method
Burning Rate ² (1.00 mm)	< 100	mm/min	FMVSS 302

Flame Rating (1.60 mm)	HB	UL 94
NOTE		
1.	10 K/min, DSC	
2.	>1 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

