

Maxxam™ PD 2201

Polypropylene

PolyOne Corporation

Message:

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Features	General Purpose		
	Medium Flow		
Uses	Construction Applications		
	Consumer Applications		
	General Purpose		
	Industrial Applications		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Specific Volume	0.954	cm ³ /g	ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.80 to 1.2	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	92		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	33.8	MPa	ASTM D638
Tensile Elongation ³ (Break)	45	%	ASTM D638
Flexural Modulus	2170	MPa	ASTM D790
Flexural Strength	50.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	37	J/m	ASTM D256A
Unnotched Izod Impact ⁴ (23°C, 3.18 mm)	400	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.18 mm)	124	°C	ASTM D648

Injection	Nominal Value	Unit
Mold Temperature	16.0 to 50.0	°C
NOTE		
1.	Procedure A	
2.	Type I, 51 mm/min	
3.	Type I, 51 mm/min	
4.	Injection Molded	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

