

POCAN® B 3225 XF 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, 20 % glass fibers, injection molding, improved flowability, improved impact strength

General Information			
UL YellowCard	E245249-100129046		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Flow		
	Good Impact Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.40	g/cm ³	ISO 1183
Apparent Density	0.65	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	35.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow : 260°C, 2.00 mm ¹	1.1	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.10	%	
Flow : 260°C, 2.00 mm ³	0.50	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	%	
Water Absorption			ISO 62
Saturation, 23°C	0.40	%	
Equilibrium, 23°C, 50% RH	0.10	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	135	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	6500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	105	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.5	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	6100	MPa	ISO 178/A
Flexural Stress			ISO 178/A
3.5% Strain,23°C	160	MPa	
23°C ⁶	165	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	3.7	%	ISO 178/A
ISO Shortname	PBT, GHMR, 07-060, GF20		ISO 7792
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	40	kJ/m ²	
23°C	60	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	40	kJ/m ²	
23°C	50	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
8.0 MPa, Unannealed	130	°C	ISO 75-2/C
Vicat Softening Temperature	205	°C	ISO 306/B120
Melting Temperature ⁸	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	2.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	1.3E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	375	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm)	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	750	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (2.00 mm)	775	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

