

Terralene® WF 6534

High Density Polyethylene

FKuR Kunststoff GmbH

Message:

High desnity polyethylene with narrow molar mass distribution, containing a medium amount of wood fibers and functional additives. Recommended for the production of injection moulded articles.

General Information			
Filler / Reinforcement	Wood Fiber		
Additive	Unspecified Additive		
Features	Narrow Molecular Weight Distribution		
	Recyclable Material		
	Renewable Resource Content		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density ¹	1.09	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0 to 4.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	26.0	MPa	
Break	25.0	MPa	
Tensile Strain			ISO 527-2
Yield	4.0	%	
Break	4.5	%	
Flexural Modulus	2620	MPa	ISO 178
Flexural Stress (3.5% Strain)	34.0	MPa	ISO 178
Flexural Strain at Break	7	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.5	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	8.0	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	130 to 145	°C	ISO 3146
NOTE			

1.

Measured on injection moulded specimen

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

