

# Hanwha Total PP GH42F

High Crystallinity Polypropylene

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

## Message:

GH42F is a fire-resistant G/F modified polypropylene compound modified by filling glass fiber to improve mechanical rigidity and heat-resistance. It also possesses excellent flame retardancy. This product can be produced modifying a variety of base PPs, including HIPP (High Isotactic Polypropylene), in HANWHA TOTAL's special processing technology. G/F modified PP is commonly used in making products such as car switch covers, electric tool housings and the like requiring high rigidity, high heat resistance and flame retardancy.

General Information			
UL YellowCard	E140331-222928		
Filler / Reinforcement	Glass fiber reinforced material		
Features	Low warpage		
	Rigidity, high		
	m-benzene dimethyl		
	Impact resistance, high		
	Workability, good		
	Heat resistance, high		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Electrical components		
	Power/other tools		
	Industrial application		
	Shell		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (2.00 mm)	0.30 - 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	103		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup>	58.8	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Apparent Bending Modulus	88.3	MPa	ASTM D747
Flexural Modulus	4900	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact (23°C)	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	161	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	180 - 220	°C	
Middle Temperature	180 - 220	°C	
Front Temperature	180 - 220	°C	
Mold Temperature	40.0 - 80.0	°C	
Injection Pressure	58.8 - 108	MPa	
Back Pressure	0.490 - 0.981	MPa	
Screw Speed	20 - 70	rpm	
Injection instructions			
Injection Speed: max			
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

