

Sup-tech H703

Polyamide 46

Shanghai Suptech Engineering Plastics Co. Ltd.

Message:

Sup-tech H703 is a Polyamide 46 (Nylon 46) product filled with 15% glass fiber. It can be processed by injection molding and is available in Asia Pacific. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.29	g/cm ³	DIN 53479
Molding Shrinkage	5.0E-3 to 0.011	%	DIN 53464
Water Absorption			DIN 53495
23°C, 24 hr	1.8	%	
Saturation, 23°C	3.0	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	135	MPa	DIN 53455
Tensile Strain (Break)	3.0	%	DIN 53452
Flexural Modulus	7300	MPa	DIN 53457
Flexural Stress	210	MPa	DIN 53457
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.5	kJ/m ²	DIN 53453
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			DIN 53461
0.45 MPa, Unannealed	270	°C	
1.8 MPa, Unannealed	220	°C	
Melting Temperature	295	°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Electric Strength	24	kV/mm	DIN 53481
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	9.0 to 18	hr	
Processing (Melt) Temp	250 to 290	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

