

Braskem PE GM 7746 CA

High Density Polyethylene

Braskem

Message:

Description:
GM7746CA is a High Density Polyethylene specially developed for the manufacturing of blow molding fuel tanks. It has high molar mass and excellent mechanical properties. Besides, it shows excellent tenacity, high resistance to stress cracking, and outstanding impact resistance. The resin contains additives to protect it against ultraviolet radiation action.

Application:
Mono and multilayer fuel tanks for trucks; sheet extrusion for pickup rear protectors.

General Information			
Additive	UV Stabilizer		
Features	Good Impact Resistance		
	Good UV Resistance		
	High ESCR (Stress Crack Resist.)		
	High Molecular Weight		
Uses	Automotive Applications		
	Fuel Tanks		
	Sheet		
Processing Method	Blow Molding		
	Sheet Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.944	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/21.6 kg)	4.5	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 2.00 mm, 100% Igepal, Compression Molded, F50)	> 1000	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Compression Molded)	62		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, Compression Molded	23.0	MPa	
Break, Compression Molded	42.0	MPa	
Tensile Elongation			ASTM D638
Yield, Compression Molded	13	%	
Break, Compression Molded	880	%	

Flexural Modulus - 1% Secant (Compression Molded)	890	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Compression Molded)	760	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	70.0	°C	ASTM D648
Vicat Softening Temperature	126	°C	ASTM D1525 ¹
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

