

NORYL™ WCA871A resin

Polyphenylene Ether

SABIC Innovative Plastics Asia Pacific

Message:

Flame retardant performance and mechanical properties capable of meeting UL VW-1 requirement and 105C temperature rating as defined UL1581. UL1581 tests conducted on 1.0mmD wire with AWG28 conductor.

General Information			
Features	Flame Retardant		
Agency Ratings	UL VW-1		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/5.0 kg)	15	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 30 sec)	87		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Break	30.0	MPa	UL 1581
Break ¹	18.0	MPa	ASTM D638
Break, 136°C ²	27.0	MPa	UL 1581
Break	18.0	MPa	ISO 527-2/50
Tensile Elongation			
Break	280	%	UL 1581
Break ³	140	%	ASTM D638
Break, 136°C ⁴	200	%	UL 1581
Break	130	%	ISO 527-2/50
Flexural Modulus ⁵			
100 mm Span	100	MPa	ASTM D790
--	100	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°C	ASTM D746
UL Temperature Rating	105	°C	UL 1581
Heat Deformation (121°C) ⁶	20	%	UL 1581
Smoke Density			ASTM E662
Flame, 0.5 mm plaque, Ds, max	140		
Non-Flame, 0.5 mm plaque, Ds, max	67		
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.4E+16	ohms · cm	ASTM D257
Electric Strength (1.50 mm, in Oil)	28	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	2.60		IEC 60250

Dissipation Factor (1 MHz)	2.8E-3		IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index (3.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (3.00 mm)	825	°C	IEC 60695-2-13
Oxygen Index	28	%	ISO 4589-2

NOTE

1. Type I, 50 mm/min
2. After 7 days
3. Type I, 50 mm/min
4. After 7 days
5. 13 mm/min
6. 250 g

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

