

Panlite® LN-3000RM

Polycarbonate

TEIJIN LIMITED

Message:

High light reflection grade, Phosphor type flame resistant grade

General Information			
UL YellowCard	E50075-241813	E244324-101516715	
Features	Flame Retardant		
	High Reflectivity		
Uses	LEDs		
	Lighting Applications		
	Reflectors		
Appearance	White		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.29	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.40 to 0.60	%	
Flow : 4.00 mm	0.40 to 0.60	%	
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3000	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	55.0	MPa	
Break	60.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	6.0	%	
Break	110	%	
Flexural Modulus ¹	2700	MPa	ISO 178
Flexural Stress ²	93.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	60	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	98.0	°C	ISO 75-2/B

1.8 MPa, Unannealed	92.0	°C	ISO 75-2/A
Vicat Softening Temperature	100	°C	ISO 306/B50
CLTE			ISO 11359-2
Flow	7.0E-5	cm/cm/°C	
Transverse	7.0E-5	cm/cm/°C	
RTI Elec (1.50 mm)	80.0	°C	UL 746
RTI Imp (1.50 mm)	80.0	°C	UL 746
RTI Str (1.50 mm)	80.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength ³	32	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.40		
1 MHz	3.40		
Dissipation Factor			IEC 60250
100 Hz	5.5E-3		
1 MHz	0.010		
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.400 mm	V-2		
0.800 mm	V-0		
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	short time test		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT