Veroplas 080

Styrene Acrylonitrile

PlastxWorld Inc.

Message:

Veroplas 080 is a Styrene Acrylonitrile (SAN) product. It can be processed by injection molding and is available in Europe or North America. Primary characteristic: heat resistant.

General Information			
UL YellowCard	E315545-100091189		
Features	High Heat Resistance		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	78.6	MPa	ASTM D638
Flexural Modulus	3720	MPa	ASTM D790
Flexural Strength	118	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	21	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed)	97.2	°C	ASTM D648
CLTE - Flow	6.8E-5	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

