

SABIC® PP 531P

Polypropylene Homopolymer
Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® PP 531P has a high molecular weight and therefore mainly used for extrusion. It can be used for non-pressure pipes and sheet applications. The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/medical applications.

General Information	
Features	High Molecular Weight Homopolymer
Uses	Piping Sheet
Forms	Pellets
Processing Method	Extrusion Pipe Extrusion Sheet Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.905	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.30	g/10 min	ASTM D1238, ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	107		ASTM D785
Shore Hardness (Shore D)	70		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
1% Secant ¹	1600	MPa	ASTM D638
--	1600	MPa	ISO 527-2/1A/1
Tensile Strength			
Yield ²	38.0	MPa	ASTM D638
Yield	37.0	MPa	ISO 527-2/1A/50
Tensile Elongation			
Yield ³	8.0	%	ASTM D638
Yield	9.0	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	2.5	kJ/m ²	
0°C	3.5	kJ/m ²	
23°C	6.0	kJ/m ²	

Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Notched Izod Impact			
-20°C	25	J/m	ASTM D256A
0°C	35	J/m	ASTM D256A
23°C	60	J/m	ASTM D256A
-20°C	2.5	kJ/m ²	ISO 180/1A
0°C	3.5	kJ/m ²	ISO 180/1A
23°C	6.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	90.0	°C	ASTM D648
0.45 MPa, Unannealed ⁴	85.0	°C	ISO 75-2/Bf
1.8 MPa, Unannealed	60.0	°C	ASTM D648
1.8 MPa, Unannealed ⁵	55.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	156	°C	ASTM D1525, ISO 306/A120 5 ⁶
--	98.0	°C	ASTM D1525, ISO 306/B120 6 ⁷
NOTE			
1.	1.0 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	testbar 80*10*4mm		
5.	testbar 80*10*4mm		
6.	Rate B (120°C/h), Loading 1 (10 N)		
7.	Rate B (120°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT