

# LONGLITE® PBT 3015-200X

Polybutylene Terephthalate

CCP Group

## Message:

PBT 3015-200X is a 15% glass fiber reinforced natural color injection molding grade.

| General Information                       |                                  |                   |             |
|-------------------------------------------|----------------------------------|-------------------|-------------|
| Filler / Reinforcement                    | Glass Fiber,15% Filler by Weight |                   |             |
| Appearance                                | Natural Color                    |                   |             |
| Processing Method                         | Injection Molding                |                   |             |
| Physical                                  | Nominal Value                    | Unit              | Test Method |
| Density                                   | 1.41                             | g/cm <sup>3</sup> | ISO 1183    |
| Melt Mass-Flow Rate (MFR) (250°C/2.16 kg) | 18                               | g/10 min          | ISO 1133    |
| Molding Shrinkage                         |                                  |                   | ISO 294-4   |
| Across Flow                               | 1.1 to 1.3                       | %                 |             |
| Flow                                      | 0.40 to 0.60                     | %                 |             |
| Mechanical                                | Nominal Value                    | Unit              | Test Method |
| Tensile Modulus (23°C)                    | 5500                             | MPa               | ISO 527-2   |
| Tensile Stress (Break, 23°C)              | 105                              | MPa               | ISO 527-2   |
| Tensile Strain (Break, 23°C)              | 3.5                              | %                 | ISO 527-2   |
| Flexural Modulus (23°C)                   | 4700                             | MPa               | ISO 178     |
| Flexural Stress (23°C)                    | 160                              | MPa               | ISO 178     |
| Impact                                    | Nominal Value                    | Unit              | Test Method |
| Charpy Notched Impact Strength (23°C)     | 6.5                              | kJ/m <sup>2</sup> | ISO 179/1eA |
| Thermal                                   | Nominal Value                    | Unit              | Test Method |
| Heat Deflection Temperature               |                                  |                   |             |
| 0.45 MPa, Unannealed                      | 215                              | °C                | ISO 75-2/B  |
| 1.8 MPa, Unannealed                       | 200                              | °C                | ISO 75-2/A  |
| Melting Temperature                       | 225                              | °C                | ISO 11357-3 |
| Electrical                                | Nominal Value                    | Unit              | Test Method |
| Surface Resistivity                       | 1.0E+14                          | ohms              | IEC 60093   |
| Volume Resistivity                        | 1.0E+15                          | ohms·cm           | IEC 60093   |
| Electric Strength (2.00 mm)               | 23                               | kV/mm             | IEC 60243-1 |
| Flammability                              | Nominal Value                    | Unit              | Test Method |
| Flame Rating                              | HB                               |                   | UL 94       |
| Injection                                 | Nominal Value                    | Unit              |             |
| Drying Temperature                        | 120 to 140                       | °C                |             |
| Drying Time                               | 4.0                              | hr                |             |
| Processing (Melt) Temp                    | 240 to 270                       | °C                |             |

|                  |             |    |
|------------------|-------------|----|
| Mold Temperature | 60.0 to 100 | °C |
|------------------|-------------|----|

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

