

BONDYRAM® 7103

Maleic Anhydride Grafted Polymer

Polyram Ram-On Industries

Message:

Maleic Anhydride modified Ethylene-Alpha Olefin Copolymer

High flow impact modifier for Polyamide compounds un-reinforced and glass fiber reinforced. Good retention of impact at low temperatures.

General Information			
Features	Copolymer		
	Low Temperature Impact Resistance		
Uses	Plastics Modification		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.880	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.5	g/10 min	ASTM D1238, ISO 1133

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

