

Orgalloy® LT 4060ES

Polyamide 6 Alloy

Arkema

Message:

Orgalloy® LT 4060ES is a Polyamide 6 Alloy (Nylon 6 Alloy) product. It can be processed by blow molding, extrusion, film extrusion, profile extrusion, or sheet extrusion and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Heat Resistant

Impact Resistant

General Information				
Features	Good Impact Resistance			
	High Heat Resistance			
	Platable			
Forms	Pellets			
Processing Method	Blow Molding			
	Extrusion			
	Film Extrusion			
	Profile Extrusion			
	Sheet Extrusion			
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)			
	Secant Modulus vs. Strain (ISO 11403-1)			
	Shear Modulus vs. Temperature (ISO 11403-1)			
	Specific Volume vs Temperature (ISO 11403-2)			
Physical	Dry	Conditioned	Unit	Test Method
Density	1040	1040	kg/m ³	ISO 1183 ¹
Melt volume-flow rate (235°C/5.0 kg)	0.500	--	cm ³ /10min	ISO 1133 ²
Water Absorption				ISO 62 ³
Saturation	5.0	--	%	
Equilibrium	1.1	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile modulus	--	300	MPa	ISO 527-2 ⁴
Tensile Stress (50% Strain)	--	22.0	MPa	ISO 527-2 ⁵
Tensile Strain (Break)	--	> 50	%	ISO 527-2 ⁶
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	60.0	--	°C	ISO 75-2 ⁷
Melting Temperature ⁸	220	--	°C	ISO 11357-3 ⁹

Electrical	Dry	Conditioned	Test Method
Comparative tracking index	--	600	IEC 60112 ¹⁰
Flammability	Dry	Conditioned	Test Method
Burning Behav. at 1.6mm nom. thickn. (1.60 mm)	HB	--	ISO 1210 ¹¹
Burning Behav. at thickness h (3.20 mm)	HB	--	ISO 1210 ¹²

NOTE

1.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
2.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
3.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
4.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
5.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
6.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
7.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
8.	10 °C/min
9.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
10.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
11.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
12.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

