

# Viprene™ P75A-22U-BLK

Thermoplastic Vulcanizate

Alliance Polymers & Services

## Message:

Viprene™ P75A-22U-BLK is a UV and Heat Stabilized TPV (thermoplastic vulcanizate elastomer). This material can be easily processed by extrusion or injection molding. It exhibits easy flowing characteristics.

General Information	
Additive	heat stabilizer UV stabilizer
Features	Good UV resistance Good liquidity Thermal Stability
Appearance	Black
Forms	Particle
Processing Method	Extrusion Injection molding

Physical	Nominal Value	Unit	Test Method
Density	0.970	g/cm <sup>3</sup>	ISO 2781
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% strain	3.10	MPa	ISO 37
300% strain	4.60	MPa	ISO 37
Tensile Stress (Break)	8.90	MPa	ISO 37
Tensile Elongation (Break)	550	%	ISO 37
Tear Strength	49	kN/m	ISO 34-1
Compression Set (70°C, 22 hr)	26	%	ASTM D395B
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-60.0	°C	ASTM D746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.00 mm	HB		UL 94
1.50 mm	HB		UL 94
3.00 mm	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	80.0	°C
Drying Time	3.0	hr
Rear Temperature	180	°C
Middle Temperature	185	°C
Front Temperature	190	°C
Nozzle Temperature	195 - 225	°C
Processing (Melt) Temp	200 - 230	°C
Mold Temperature	10.0 - 50.0	°C
Back Pressure	0.500 - 0.850	MPa
Screw Speed	100 - 200	rpm
Clamp Tonnage	4.0 - 7.0	kN/cm <sup>2</sup>

#### Injection instructions

Injection Speed: 50 mm/sec or more

Extrusion	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	180	°C
Cylinder Zone 2 Temp.	190	°C
Cylinder Zone 3 Temp.	195	°C
Die Temperature	205	°C

#### Extrusion instructions

Gate Temperature: 200°C (392°F) Die Pressure: 4.8 to 17 MPa (696 to 2465 psi)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

