

POLIMAXX 2300NC

Polypropylene Impact Copolymer

IRPC Public Company Limited

Message:

2300NC is a Polypropylene Block Copolymer resin for injection molding process with medium flow, good impact resistance characteristic. It is suitable for any applications that need high impact strength such as auto parts, electrical parts, toy and containers. It also meets the F.D.A. requirement in the code of federal regulations in 21 CFR 177.1520 for food contact.

General Information			
UL YellowCard	E132283-222108		
Features	Block Copolymer		
	Food Contact Acceptable		
	High Impact Resistance		
	Medium Flow		
Uses	Automotive Applications		
	Containers		
	Electrical Parts		
	Toys		
Agency Ratings	FDA 21 CFR 177.1520		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	98		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	28.0	MPa	ASTM D638
Tensile Elongation (Yield)	20	%	ASTM D638
Flexural Modulus - 1% Secant	1300	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.8	kJ/m²	DIN 53453
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	98.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 to 240	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT