

BESTPOLUX PCG2X/01

Polycarbonate

Triesa Plastics

Message:

Polycarbonate natural lubrified with 10% glass fibre reinforcement and V-0 quality.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Additive	Lubricant		
Features	Lubricated		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ISO 1183
Molding Shrinkage	0.35	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.12	%	ISO 62
Humidity - Pellets	0.20	%	ISO 1110
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3300	MPa	ISO 527-2
Tensile Stress	80.0	MPa	ISO 527-2
Tensile Strain (Break)	6.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.5	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength			ISO 179
-40°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	150	°C	ISO 75-2/B
1.8 MPa, Unannealed	145	°C	ISO 75-2/A
Vicat Softening Temperature	> 145	°C	ISO 306
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+15	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	2.0 to 4.0	hr	

Processing (Melt) Temp	260 to 280	°C
Mold Temperature	80.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

