

Multi-Flex® TPE A5001 LC

Thermoplastic Elastomer

Multibase, A Dow Corning Company

Message:

Multi-Flex® TPE A5001 LC is a Thermoplastic Elastomer (TPE) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

General Information			
Features	Low Compression Set		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.921	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	47		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	7.18	MPa	ASTM D412
Tensile Elongation (Break)	630	%	ASTM D412
Tear Strength	21.2	kN/m	ASTM D624
Compression Set			ASTM D395
23°C, 22 hr	16	%	
70°C, 22 hr	36	%	
100°C, 22 hr	46	%	
Injection	Nominal Value	Unit	
Drying Temperature	65.6	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	188	°C	
Middle Temperature	191	°C	
Front Temperature	196	°C	
Nozzle Temperature	196	°C	
Processing (Melt) Temp	196	°C	
Mold Temperature	26.7 to 43.3	°C	
Injection Rate	Moderate-Fast		
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	188	°C	
Cylinder Zone 3 Temp.	193	°C	
Cylinder Zone 5 Temp.	199	°C	
Melt Temperature	199	°C	
Die Temperature	202	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

