

OmniCarb™ PC/ABS 1228

Polycarbonate + ABS

OMNI Plastics, LLC

Message:

High Impact, Easy Flow PC/ABS

General Information			
Features	Good Flow		
	High Impact Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	28	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	56.5	MPa	ASTM D638
Tensile Elongation (Break)	> 50	%	ASTM D638
Flexural Modulus	2520	MPa	ASTM D790
Flexural Strength	93.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	98.9	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (3.18 mm)	HB		Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	104	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	227 to 260	°C	
Middle Temperature	238 to 282	°C	
Front Temperature	238 to 282	°C	
Nozzle Temperature	238 to 282	°C	
Processing (Melt) Temp	238 to 282	°C	
Mold Temperature	26.7 to 104	°C	
Back Pressure	0.345 to 0.689	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT