

RTP 128 HI Z

Polypropylene
RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Impact resistance, high		
Agency Ratings	FDA not rated		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.1	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.030	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2070	MPa	ASTM D638
Tensile Strength	17.9	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790
Flexural Strength	31.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	270	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1200	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	116	°C	ASTM D648
1.8 MPa, not annealed	77.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Additional Information			
Mold Shrinkage, ASTM D955, 0.250 in: 18 mil/inTensile Elongation, ASTM D638: >10%			
Injection	Nominal Value	Unit	

Rear Temperature	218 - 274	°C
Middle Temperature	218 - 274	°C
Front Temperature	218 - 274	°C
Mold Temperature	32.2 - 65.6	°C
Injection Pressure	68.9 - 103	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT