

GLS Nylon 66 LKG36

Polyamide 66
GLS Polymers Pvt. Ltd.

Message:
Nylon66 15 PTFE 30 GF Precolor

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
	PTFE Fiber,15% Filler by Weight		
Appearance	Colors Available		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23 to 1.24	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	1.5 to 3.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	> 2800	MPa	ASTM D638
Tensile Strength ¹ (Yield)	> 66.0	MPa	ASTM D638
Flexural Modulus	> 2400	MPa	ASTM D790
Flexural Strength	> 96.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	> 48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	76.0 to 80.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (3.00 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	275 to 298	°C	
Mold Temperature	67.0 to 106	°C	
Injection Pressure	68.0 to 128	MPa	
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

