

Witcom PA66 8LC-HS

Polyamide 66

Witcom Engineering Plastics B.V.

Message:

Witcom PA66 8LC-HS is a polyamide 66 (nylon 66) product that contains 40% long carbon fiber as filler. It can be processed by injection molding and is available in Europe. The main characteristics are: flame retardant/rated flame.

General Information			
Filler / Reinforcement	Long carbon fiber, 40% filler by weight		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183
Molding Shrinkage - Flow (3.00 mm)	0.10 - 0.30	%	ISO 2577
Water Absorption			ISO 62
Saturated, 23°C	5.1	%	ISO 62
Equilibrium, 23°C, 50% RH	1.5	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	34000	MPa	ISO 527-2
Tensile Stress (Yield)	< 310	MPa	ISO 527-2
Tensile Strain (Break)	1.0 - 2.0	%	ISO 527-2
Flexural Modulus	33000	MPa	ISO 178
Flexural Stress	460	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	22	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength	65	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	250	°C	ISO 75-2/A
CLTE - Flow	1.9E-5	cm/cm/°C	ISO 11359-2
RTI Imp (3.00 mm)	105	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	10 - 1.0E+3	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (3.00 mm)	HB		IEC 60695-11-10, -20
Glow Wire Flammability Index (1.60 mm)	750	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0 - 8.0	hr	
Suggested Max Moisture	0.10	%	
Processing (Melt) Temp	275 - 295	°C	
Mold Temperature	95.0 - 170	°C	

Injection Rate	Fast	
Back Pressure	0.00 - 1.00	MPa
Injection instructions		

Screw speed: 0.1 - 0.2 m/sInjection pressure: Keep to a minimumHold pressure: Keep to a minimum

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

