

KEBAFORM® C 902 UR

Acetal (POM) Copolymer

BARLOG plastics GmbH

Message:

POM Copolymer unreinforced, impact modified

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
Resin ID (ISO 1043)	POM-I		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.8	%	
Flow	1.8	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2050	MPa	ISO 527-2
Tensile Stress (Yield)	50.0	MPa	ISO 527-2
Tensile Strain (Yield)	14	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	95.0	°C	ISO 75-2/A
Melting Temperature ¹	166	°C	ISO 11357-3
Flammability	Nominal Value		Test Method
Flammability Classification	HB		IEC 60695-11-10, -20
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

