

Starex WR-9130

Acrylonitrile Styrene Acrylate

SAMSUNG SDI CO., LTD.

Message:

Starex WR-9130 is an Acrylonitrile Styrene Acrylate (ASA) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
UL YellowCard	E115797-219511		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	103		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	28.2	MPa	ASTM D638
Tensile Elongation ² (Break)	110	%	ASTM D638
Flexural Modulus ³	1770	MPa	ASTM D790
Flexural Strength ⁴	56.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	15	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	84.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature			
--	80.0 to 90.0	°C	
Desiccant Dryer	80.0	°C	
Drying Time			
--	2.0 to 4.0	hr	
Desiccant Dryer	2.0 to 3.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	180 to 190	°C	
Middle Temperature	200 to 210	°C	
Front Temperature	220 to 230	°C	
Nozzle Temperature	240	°C	
Mold Temperature	40.0 to 80.0	°C	

Injection Pressure	49.0 to 245	MPa
Back Pressure	0.490 to 1.96	MPa
Screw Speed	50 to 150	rpm

NOTE		
1.	5.0 mm/min	
2.	5.0 mm/min	
3.	2.8 mm/min	
4.	2.8 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT