

TECHNYL® 1021GF6 BRIGHT

Polyamide 6
Solvay Engineering Plastics

Message:

TECHNYL 1021GF6 BRIGHT is a polyamide 6, 30% glass fiber reinforced, for injection molding. This product is available in bright color.

General Information				
Filler / Reinforcement	Glass Fiber,30% Filler by Weight			
Agency Ratings	UU 453/2010/EC			
RoHS Compliance	RoHS Compliant			
Appearance	Colors Available			
Processing Method	Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm ³	ISO 1183/A
Molding Shrinkage	Internal Method			
Across Flow	0.65	--	%	
Flow	0.35	--	%	
Water Absorption (23°C, 24 hr)	0.95	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	121	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength (Yield)	175	--	MPa	ASTM D638
Tensile Elongation (Break)	3.5	--	%	ASTM D638
Flexural Modulus	8900	--	MPa	ASTM D790
Flexural Strength	260	--	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact	130	--	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	210	--	°C	ASTM D648
Melting Temperature	222	--	°C	ISO 11357-3
CLTE - Flow (23 to 85°C)	3.2E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+11	ohms·cm	IEC 60093
Electric Strength	--	22	kV/mm	IEC 60243-1
Dissipation Factor	0.020	0.090		IEC 60250
Comparative Tracking Index (Solution A)	550	475	V	IEC 60112

Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating	HB	--		UL 94
Glow Wire Flammability Index (1.60 mm)	650	--	°C	IEC 60695-2-12
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	230 to 235		°C	
Middle Temperature	235 to 245		°C	
Front Temperature	245 to 250		°C	
Mold Temperature	80.0 to 100		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

