

XIRAN® SZ26120

Styrene Maleic Anhydride

Polyscope Polymers BV

Message:

XIRAN® SZ26120 is an amorphous thermoplastic random SMA (styrene maleic anhydride) copolymer. XIRAN® SZ26120 is typically added to other engineering plastics to increase:

- thermal stability
- dimensional stability
- surface adhesion properties

Application areas

XIRAN® SZ26120 is specifically designed as high heat modifier for PMMA and ABS and as dispersant for pigments, fillers and flame retardants in many polymer matrices.

General Information			
Features	Good dimensional stability		
	Copolymer		
	Good adhesion		
	Thermal stability, good		
	amorphous		
Uses	High temperature application		
	Plastic modification		
Appearance	White		
	Clear/transparent		
Forms	Particles		
Processing Method	Composite		
	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Apparent Density	0.60	g/cm ³	Internal method
Maleic Anhydride Content	26	%	Internal method
Molecular Weight	120000	g/mol	Internal method
Moisture Content		ppm	ISO 760
Pellet Size	4.00	mm	
Polydispersity - (Mw/Mn)	2.50		ISO 13885-1
Volatiles		ppm	GC
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	160	°C	ISO 3146

Vicat Softening Temperature	155	°C	ISO 306
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	230 - 250	°C	
Middle Temperature	230 - 250	°C	
Front Temperature	230 - 250	°C	
Processing (Melt) Temp	< 280	°C	
Injection instructions			
Optimum processing temperature: 240-270°C			
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Cylinder Zone 1 Temp.	230 - 250	°C	
Cylinder Zone 2 Temp.	230 - 250	°C	
Cylinder Zone 3 Temp.	230 - 250	°C	
Cylinder Zone 4 Temp.	230 - 250	°C	
Cylinder Zone 5 Temp.	230 - 250	°C	
Extrusion instructions			
Optimum processing temperature: 240-270°CMaximum processing temperature: 280°C			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

