

RTP 903 Z

Polysulfone

RTP Company

Message:

Glass Fiber - FDA Compliant Ingredients

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.30	%	ASTM D955
Moisture Content	0.15	%	
Primary Additive	20	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5170	MPa	ASTM D638
Tensile Strength	89.6	MPa	ASTM D638
Tensile Elongation (Yield)	3.5	%	ASTM D638
Flexural Modulus	5170	MPa	ASTM D790
Flexural Strength	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	80	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	640	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	188	°C	
1.8 MPa, Unannealed	182	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+12	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	135	°C	
Drying Time	4.0	hr	
Dew Point	-31.7	°C	
Processing (Melt) Temp	332 to 371	°C	

Mold Temperature	93.3 to 149	°C
Injection Pressure	68.9 to 124	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

