

Arnitel® VT3104

Thermoplastic Elastomer

DSM Engineering Plastics

Message:

Arnitel® VT3104 is a Thermoplastic Elastomer (TPE) material. It is available in Asia Pacific, Europe, or North America for extrusion. Primary attribute of Arnitel® VT3104: Flame Rated.

General Information			
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	13.5	cm ³ /10min	ISO 1133
Water Absorption			ISO 62
Saturation, 23°C	7.0	%	
Equilibrium, 23°C, 50% RH	0.40	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 3 sec)	32		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	60.0	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Break	13.1	MPa	
10% Strain	4.40	MPa	
50% Strain	8.80	MPa	
100% Strain	10.9	MPa	
Nominal Tensile Strain at Break	200	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	212	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.5E-4	cm/cm/°C	
Transverse	1.5E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Electric Strength	20	kV/mm	IEC 60243-1

Relative Permittivity		IEC 60250	
100 Hz	4.70		
1 MHz	4.40		
Dissipation Factor		IEC 60250	
100 Hz	0.031		
1 MHz	0.081		
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (1.60 mm)	HB		IEC 60695-11-10, -20
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

