

Stanyl® TE200F8

Polyamide 46
DSM Engineering Plastics

Message:

Stanyl® TE200F8 is a Polyamide 46 (Nylon 46) material filled with 40% glass fiber. It is available in North America.
Important attributes of Stanyl® TE200F8 are:
Flame Rated
Heat Stabilizer
Typical application of Stanyl® TE200F8: Electrical/Electronic Applications

General Information				
Filler / Reinforcement		Glass Fiber,40% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
Uses		Electrical/Electronic Applications		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.51	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.1	--	%	
Flow	0.50	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	2.2	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2
--	13000	8000	MPa	
120°C	6900	--	MPa	
160°C	6100	--	MPa	
180°C	5700	--	MPa	
200°C	5300	--	MPa	
Tensile Stress				ISO 527-2
Break	230	140	MPa	
Break, 120°C	130	--	MPa	
Break, 160°C	115	--	MPa	
Break, 180°C	105	--	MPa	
Break, 200°C	100	--	MPa	
Tensile Strain				ISO 527-2
Break	3.0	6.0	%	
Break, 120°C	6.5	--	%	
Break, 160°C	6.5	--	%	
Break, 180°C	6.5	--	%	
Break, 200°C	6.5	--	%	

Flexural Modulus				ISO 178
--	11500	7000	MPa	
120°C	5800	--	MPa	
160°C	5200	--	MPa	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	12	12	kJ/m ²	
23°C	14	21	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	75	85	kJ/m ²	
23°C	95	100	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
-40°C	12	12	kJ/m ²	
23°C	14	21	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)				
	290	--	°C	ISO 75-2/A
Melting Temperature	295	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	2.5E-5	--	cm/cm/°C	
Transverse	5.0E-5	--	cm/cm/°C	
Thermal Index - 5000 hr	159	--	°C	IEC 60216
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	> 1.0E+15	1.0E+12	ohms·cm	IEC 60093
Electric Strength	35	25	kV/mm	IEC 60243-1
Comparative Tracking Index	400	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.750 mm	HB	--		
1.50 mm	HB	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	280 to 320		°C	
Middle Temperature	300 to 320		°C	
Front Temperature	300 to 320		°C	
Nozzle Temperature	300 to 320		°C	
Processing (Melt) Temp	305 to 320		°C	
Mold Temperature	80.0 to 120		°C	

Injection Rate	Moderate-Fast	
Back Pressure	2.00 to 10.0	MPa
Screw Compression Ratio	2.5:1.0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

