

RESOLE RX®643

Phenolic

Vyncolit N.V.

Message:

RESOLE RX®643 is a phenolic (Phenolic) material, and its filler is glass fiber reinforced material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing methods are: resin transfer molding, compression molding or injection molding.

RESOLE RX®The main features of the 643 are:

- chemical resistance
- high strength
- Creep resistance
- Good dimensional stability
- Good toughness

Typical application areas include:

- Electrical/electronic applications
- engineering/industrial accessories
- electrical appliances
- House
- Tools

General Information	
Filler / Reinforcement	Glass fiber reinforced material
Features	Ultra high toughness
	Good dimensional stability
	Low smoke
	High strength
	Antibacterial property
	Solvent resistance
	Good creep resistance
	alkali resistance
	acid resistance
Uses	Membrane key switch
	Pump parts
	Gear
	Electrical/Electronic Applications
	Electrical appliances
	Power/other tools
	Connector
	Application in Automobile Field
	Shell
Agency Ratings	ASTM D 5948, Type GPI-10
Forms	Particles
Processing Method	Resin transfer molding

Compression molding

Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.75	g/cm ³	ASTM D792, ISO 1183
Bulk Factor	2.1		ASTM D1895
Molding Shrinkage			
Flow: Molding	0.15	%	ASTM D955
Flow direction	0.15	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.050	%	ASTM D570, ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
E scale	85		ASTM D785
E scale	90		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			
Fracture	80.0	MPa	ISO 527-2
--	96.5	MPa	ASTM D638
Flexural Modulus			
--	13800	MPa	ASTM D790
--	15000	MPa	ISO 178
Flexural Strength			
--	186	MPa	ASTM D790
--	150	MPa	ISO 178
Compressive Strength	234	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
--	59	J/m	ASTM D256A
--	4.5	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	282	°C	ASTM D648, ISO 75-2/A
CLTE - Flow	1.3E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.50	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength			
-- ¹	14	kV/mm	ASTM D149
-- ²	11	kV/mm	ASTM D149
--	14	kV/mm	IEC 60243-1
Arc Resistance	135	sec	ASTM D495
Injection	Nominal Value	Unit	Test Method
Rear Temperature	60.0	°C	

Middle Temperature	73.9	°C
Nozzle Temperature	87.8	°C
Processing (Melt) Temp	98.9 - 116	°C
Mold Temperature	166 - 188	°C
Back Pressure	0.207	MPa

Injection instructions

Plastication: 50rpm Injection Pressure: Set to give 3 to 5 seconds injection time Hold Pressure: 50 to 100% of injection pressure Hold Time: 10 sec minimum Cure Time, 0.125 in: 30 to 35 sec The value listed as Thermal Conductivity, ASTM C177, was tested in accordance with ASTM C518. The value listed as Molding Shrinkage, ISO 294-4, was tested in accordance with ISO 2577 using compression molded specimens. Water Absorption, ASTM D570, 48 hrs, 50°C: 0.3% Flexural Strain, ASTM D790: 1.4% DTUL @264psi - Unannealed, ASTM D648, Post Baked: 550°F Dielectric Strength, ASTM D149, 60 Hz, Method A, wet: 350 V/mil Dielectric Strength, ASTM D149, 60 Hz, Method B, wet: 290 V/mil Compressive Strength, ISO 604: 330 MPa Dielectric Strength, IEC 243, Method A, wet: 13.5 V/mil Compression and Transfer Molding Conditions:
 Preforming Pressure: 8000 to 12000 psi
 Preheat Temperature: 210 to 235 °F
 Preheat Time: 45 sec
 Mold Temperature: 330 to 360 °F
 Compression Mold Pressure: 2500 to 5000 psi
 Transfer Mold Pressure: 4000 to 6000 psi
 Cure Time, 0.125 in: 40 to 50 sec

NOTE

1. Method A (short time)
2. Method B (step by step)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

