

NORYL™ FE1520PW resin

Polyphenylene Ether + PS

SABIC Innovative Plastics Europe

Message:

NORYL FE1520PW resin is a blend of polyphenylene ether (PPE) and polystyrene (PS) resin that contains 20% glass reinforcement. The resin is suitable for injection molding. NORYL FE1520PW resin has been developed for fluid engineering applications that require improved hydrolytic stability. NORYL FE520PW resin has been certified for potable water applications up to 85C in Europe and North America in limited colors.

General Information			
UL YellowCard	E45329-101519378		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Hydrolytically Stable		
Uses	Potable Water Applications		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (280°C/10.0 kg)	22.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Flow : 3.20 mm	0.20 to 0.40	%	
Across Flow : 3.20 mm	0.30 to 0.60	%	
Water Absorption			
Saturation, 23°C	0.20	%	ISO 62
Equilibrium, 50% RH	0.060	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	220	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	7110	MPa	ASTM D638
--	7180	MPa	ISO 527-2/1
Tensile Strength			
Break ²	119	MPa	ASTM D638
Break	119	MPa	ISO 527-2/5
Tensile Elongation			
Break ³	2.6	%	ASTM D638
Break	2.6	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁴	6970	MPa	ASTM D790
-- ⁵	6040	MPa	ISO 178
Flexural Stress			

--	165	MPa	ISO 178
Break, 50.0 mm Span ⁶	175	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	65.0	mg	Internal Method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
-30°C ⁷	5.0	kJ/m ²	ISO 179/1eA
-30°C	27	kJ/m ²	ISO 179/2C
23°C	6.0	kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength ⁸ (23°C)	30	kJ/m ²	ISO 179/1eU
Notched Izod Impact			
-30°C	45	J/m	ASTM D256
23°C	65	J/m	ASTM D256
-30°C ⁹	4.0	kJ/m ²	ISO 180/1A
23°C ¹⁰	6.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
-30°C	400	J/m	ASTM D4812
23°C	400	J/m	ASTM D4812
-30°C ¹¹	23	kJ/m ²	ISO 180/1U
23°C ¹²	25	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 100 mm Span ¹³	132	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 3.20 mm	135	°C	ASTM D648
1.8 MPa, Unannealed, 100 mm Span ¹⁴	139	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	150	°C	ISO 306/A50
--	144	°C	ISO 306/B120
CLTE			
Flow : -40 to 40°C	3.0E-5	cm/cm/°C	
Transverse : -40 to 40°C	7.0E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	250 to 270	°C	
Middle Temperature	270 to 290	°C	
Front Temperature	290 to 310	°C	
Nozzle Temperature	280 to 300	°C	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	80.0 to 120	°C	

NOTE	
1.	5.0 mm/min
2.	Type I, 5.0 mm/min
3.	Type I, 5.0 mm/min
4.	1.3 mm/min
5.	2.0 mm/min
6.	1.3 mm/min
7.	80*10*4 sp=62mm
8.	80*10*4 sp=62mm
9.	80*10*4
10.	80*10*4
11.	80*10*4
12.	80*10*4
13.	120*10*4 mm
14.	120*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

