

Utomer UT1CP95AC

Thermoplastic Polyurethane Elastomer (Polyester)

Shanghai Utomer Material Science Co., Ltd.

Message:

TYPE: Utomer UT1CP95AC TPU is a 95A Polyether-type TPU
Features: Excellent clarity and UV stable with good melt strength.
Uses: Injection for 3 c electronic products or shoe part.

General Information			
Features	Good Melt Strength		
	Good UV Resistance		
	High Clarity		
Uses	Electrical/Electronic Applications		
	Footwear		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	93 to 97		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	< 45.0	mm ³	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	> 9.00	MPa	
300% Strain	> 19.0	MPa	
Tensile Strength	> 30.0	MPa	ASTM D412
Tensile Elongation (Break)	> 500	%	ASTM D412
Tear Strength	> 0.110	kN/m	ASTM D624
Compression Set			ASTM D395B
23°C, 70 hr	< 38	%	
70°C, 24 hr	< 45	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-15.0	°C	ASTM D3418
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	20	hr	
Rear Temperature	190	°C	
Middle Temperature	195	°C	
Front Temperature	200	°C	

Nozzle Temperature	205	°C
Mold Temperature	50.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

