

Isocor™ HG26SI

Polyamide 612

Shakespeare Monofilaments and Specialty Polymers

Message:

ISOCOR™ HG26SI is a medium viscosity PA-612 based nylon. This resin is specifically suited for applications requiring low-moisture regain and greater dimensional stability. ISOCOR™ HG26SI is used in applications requiring good electrical insulation properties. This resin can be processed using conventional techniques.

Typical applications for HG26SI include:

Cable Jacketing

Bristles

Extrusion

Tubing

Films

General Information				
Features	Good dimensional stability			
	Low hygroscopicity			
	Insulation			
	Medium viscosity			
Uses	Films			
	Cable sheath			
	Pipe fittings			
	Insulating material			
Forms	Particle			
Processing Method	Extrusion			
	Injection molding			
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.04	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.2	--	%	ASTM D955
Water Absorption (24 hr)	1.2	--	%	ASTM D570
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2300	2230	MPa	ASTM D638
Tensile Strength	31.4	31.4	MPa	ASTM D638
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact	37	39	J/m	ASTM D256
Dart Drop Impact	36.2	36.2	J	ASTM D3029
Thermal	Dry	Conditioned	Unit	Test Method
Melting Temperature	218	--	°C	DSC
Additional Information				

干燥

Color, ASTM D1003-97: 69.03 LColor, ASTM D1003-97: -2.17 aColor, ASTM D1003-97: -7.61 b

Injection	Dry	Unit
Dew Point	< -17.8	°C
Suggested Max Moisture	0.20	%
Hopper Temperature	79.4	°C
Rear Temperature	221 - 243	°C
Middle Temperature	227 - 260	°C
Front Temperature	238 - 271	°C
Nozzle Temperature	238 - 271	°C
Processing (Melt) Temp	238 - 271	°C
Mold Temperature	10.0 - 93.3	°C
Injection Pressure	3.45 - 13.8	MPa
Injection Rate	Fast	
Back Pressure	0.345	MPa
Extrusion	Dry	Unit
Suggested Max Moisture	0.10	%
Hopper Temperature	79.4	°C
Cylinder Zone 1 Temp.	254	°C
Cylinder Zone 2 Temp.	266	°C
Cylinder Zone 3 Temp.	271	°C
Cylinder Zone 4 Temp.	271	°C
Die Temperature	271	°C
Extrusion instructions		

Flange: 500°F (260°C)Air Dew Point (max): 0°F (-18°C)Neck: 500°F (260°C)Head: 480°F (250°C)Pump: 480°F (250°C)L/D Ratio: 24 to 30:1Compression Ratio: 3.5:1Polymer @ Die: 430°F (220°C)Screw Pressure: 2000 psi

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT