

Complet® LBF40-PA66

Polyamide 66

PlastiComp, Inc.

Message:

Complet® LBF40-PA66 is a polyamide 66 (nylon 66) product containing a 40% basalt fiber. It is available in North America, Europe or Asia Pacific. The main features are: Rohs certification.

General Information			
Filler / Reinforcement	Basalt Fiber, 40% filler by weight		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11000	MPa	ASTM D638
Tensile Strength	207	MPa	ASTM D638
Tensile Elongation (Break)	2.0 - 3.0	%	ASTM D638
Flexural Modulus	9100	MPa	ASTM D790
Flexural Strength	286	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	1400	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	254	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	85.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.18	%	
Suggested Max Regrind	5	%	
Rear Temperature	282 - 299	°C	
Middle Temperature	288 - 304	°C	
Front Temperature	293 - 310	°C	
Nozzle Temperature	288 - 304	°C	
Processing (Melt) Temp	293 - 310	°C	
Mold Temperature	93.3	°C	
Back Pressure	0.172 - 0.345	MPa	
Screw Speed	30 - 50	rpm	
Cushion	6.35	mm	
Screw L/D Ratio	18.0:1.0 to 20.0:1.0		
Screw Compression Ratio	2.0 : 1.0 - 3.0 : 1.0		
Injection instructions			

Injection speed: 2 to 3 in/secInjection pressure: medium to maximum

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

