

Sarlink® TPE ML-1140B BLK X (PRELIMINARY DATA)

Thermoplastic Elastomer
Teknor Apex Company

Message:
Sarlink ML-1140B BLK X is a general purpose TPE designed for automotive interior applications. This is a low hardness, high density grade suitable for injection molding.

General Information			
Features	Sunlight Resistant		
	High specific gravity		
	High density		
	Low liquidity		
	Fill		
	Hardness, low		
	UV absorption		
Uses	Washer		
	Application in Automobile Field		
	Car interior parts		
	General		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.1	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ISO 868
Shore A, 1 second, injection molding	44		ISO 868
Shore A, 5 seconds, injection molding	41		ISO 868
Shore A, 15 seconds, injection molding	39		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹			ISO 37
Transverse flow: 100% strain	0.800	MPa	ISO 37
Flow: 100% strain	1.20	MPa	ISO 37
Tensile Stress ²			ISO 37

Transverse flow: Fracture	4.30	MPa	ISO 37
Flow: Fracture	3.40	MPa	ISO 37
Tensile Elongation ³			ISO 37
Transverse flow: Fracture	890	%	ISO 37
Flow: Fracture	750	%	ISO 37
Tear Strength ⁴			ISO 34-1
Transverse flow	17	kN/m	ISO 34-1
Flow	18	kN/m	ISO 34-1
Compression Set ⁵			ISO 815
23°C, 22 hr	22	%	ISO 815
70°C, 22 hr	37	%	ISO 815
90°C, 70 hr	69	%	ISO 815
125°C, 70 hr	94	%	ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁶			ISO 188
Transverse flow: 110°C, 1008 hr	23	%	ISO 188
Flow: 110°C, 1008 hr	35	%	ISO 188
Transverse flow: 100% strain 110°C, 1008 hr	2.5	%	ISO 188
Flow: 100% strain 110°C, 1008 hr	0.0	%	ISO 188
Transverse flow: 125°C, 168 hr	26	%	ISO 188
Flow: 125°C, 168 hr	35	%	ISO 188
Transverse flow: 100% strain 125°C, 168 hr	-3.8	%	ISO 188
Flow: 100% strain 125°C, 168 hr	-0.83	%	ISO 188
Change in Tensile Strain at Break in Air ⁷			ISO 188
Transverse flow: 110°C, 1008 hr	10	%	ISO 188
Flow: 110°C, 1008 hr	18	%	ISO 188
Transverse flow: 125°C, 168 hr	15	%	ISO 188
Flow: 125°C, 168 hr	25	%	ISO 188
Change in Shore Hardness in Air			
Support a, 110°C, 1008 hr ⁸	-0.60		ISO 188
Support a, 110°C, 1008 hr ⁹	-0.70		ISO 188
Support a, 110°C, 1008 hr ¹⁰	-2.2		ISO 188
Support a, 125°C, 168 hr ¹¹	0.10		ISO 188
Support a, 125°C, 168 hr ¹²	-1.1		ISO 188
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 206 sec ⁻¹)	134	Pa · s	ASTM D3835
Additional Information	Nominal Value	Unit	Test Method
Xenon Weatherometer			SAE J1885
Delta E - 1250 kJ	0.280		SAE J1885
Delta E - 2500 kJ	0.220		SAE J1885
Injection	Nominal Value	Unit	

Rear Temperature	171 - 193	°C
Middle Temperature	177 - 199	°C
Front Temperature	182 - 204	°C
Nozzle Temperature	188 - 210	°C
Processing (Melt) Temp	188 - 210	°C
Mold Temperature	25.0 - 65.6	°C
Injection Pressure	1.38 - 6.89	MPa
Injection Rate	Moderate-Fast	
Back Pressure	0.172 - 0.345	MPa
Screw Speed	50 - 100	rpm
Cushion	3.81 - 25.4	mm

Injection instructions

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

NOTE

- | | |
|-----|--|
| 1. | Type 1, 510mm/min |
| 2. | Type 1, 510mm/min |
| 3. | Type 1, 510mm/min |
| 4. | B method, right angle specimen
(without cut), 510mm/min |
| 5. | Type a |
| 6. | Type 1 |
| 7. | Type 1 |
| 8. | 5 sec |
| 9. | 15 sec |
| 10. | 1 sec |
| 11. | 15 sec |
| 12. | 1 sec |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT