

NOVAREX® 7022R

Polycarbonate

Mitsubishi Engineering-Plastics Corp

Message:

NOVAREX® 7022R is a polycarbonate (PC) material. This product is available in the Asia-Pacific region. NOVAREX® The main characteristics of 7022R are: low viscosity.

General Information			
UL YellowCard	E53664-243600		
Features	Low viscosity		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	13.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction	0.60	%	ISO 294-4
Flow direction	0.60	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ISO 527-2
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.9	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	%	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	93.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	67	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	124	°C	ISO 75-2/A
Linear thermal expansion coefficient			ISO 11359-2
Flow	6.5E-5	cm/cm/°C	ISO 11359-2
Lateral	6.6E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Strength	17	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.10		IEC 60250
1 MHz	3.10		IEC 60250

Dissipation Factor		IEC 60250
100 Hz	6.0E-4	IEC 60250
1 MHz	9.0E-3	IEC 60250
Comparative Tracking Index (CTI)		UL 746

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

