

WPP TPO TPO-2562 P Black

Compounded Polypropylene
Washington Penn Plastic Co. Inc.

Message:

WPP TPO TPO-2562 P Black is a composite polypropylene product. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: automotive industry.
Features include:
Hard
Good toughness
Impact resistance
soft

General Information			
Features	Impact resistance, good		
	Sprayable		
	Good toughness		
	ductility		
	Medium hardness		
Uses	Application in Automobile Field		
	Strap		
Appearance	Black		
	Available colors		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.918	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	15.0	MPa	ASTM D638
Tensile Elongation ² (Break)	500	%	ASTM D638
Flexural Modulus - Tangent ³	650	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	500	J/m	ASTM D256
Instrumented Dart Impact ⁴ (-30°C)	20.0	J	ASTM D3763
Additional Information			
Tensile Elongation at Break, ASTM D638, 50mm/min: >500%			
Injection	Nominal Value	Unit	
Drying Temperature	71.1 - 87.8	°C	
Drying Time	1.0	hr	

Rear Temperature	199 - 210	°C
Middle Temperature	210 - 216	°C
Front Temperature	216 - 227	°C
Nozzle Temperature	210 - 227	°C
Mold Temperature	15.6 - 48.9	°C
Injection Pressure	4.14 - 9.65	MPa
Holding Pressure	1.72 - 4.83	MPa
Back Pressure	0.517 - 1.03	MPa
Clamp Tonnage	3.4 - 5.5	kN/cm ²
Cushion	3.18 - 6.35	mm

Injection instructions

Injection Speed: 0.25 to 2.5 in/s Zone 4 Temperature: 420 to 450°F Hot Runner Temperature: 420 to 460°F Hydraulic Oil Temperature: 110 to 125°F Shot Capacity vs. Barrel Capacity: 2.5 to 4 Screw Decompression: 0.1 to 0.25 in

NOTE

- | | |
|----|------------|
| 1. | 50 mm/min |
| 2. | 50 mm/min |
| 3. | 33 mm/min |
| 4. | 2.20 m/sec |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT