

Durethan® BM 240 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 40 % mineral, injection molding, isotropic properties, low tendency to warp

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 40% filler by weight		
Features		Good Isotropy		
		Low warpage		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.46	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 3.00mm ¹	1.2	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 3.00mm ²	0.20	--	%	ISO 2577
Flow direction: 280°C, 3.00mm ³	1.3	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 3.00mm ⁴	0.17	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	6.0	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.9	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	205	85.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C	5630	2140	MPa	ASTM D638
23°C	5800	2200	MPa	ISO 527-2/1
Tensile Strength				
Fracture, 23°C	82.7	53.1	MPa	ASTM D638
Fracture, 23°C	85.0	55.0	MPa	ISO 527-2/5
Tensile Elongation (Break, 23°C)	10	40	%	ASTM D638, ISO 527-2/5
Flexural Modulus				
23°C	5600	2000	MPa	ASTM D790

23°C ⁵	5500	2000	MPa	ISO 178/A
Flexural Strength				
23°C	150	64.8	MPa	ASTM D790
3.5% strain, 23°C	145	60.0	MPa	ISO 178/A
23°C ⁶	150	65.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	5.0	8.0	%	ISO 178/A
ISO Shortname	PA 6, MHR, 14-060, MD40	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				
				ISO 179/1eA
-40°C	< 10	< 10	kJ/m ²	ISO 179/1eA
-30°C	< 10	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				
				ISO 179/1eU
-30°C	80	80	kJ/m ²	ISO 179/1eU
23°C	140 kJ/m ²	No Break		ISO 179/1eU
Notched Izod Impact				
				ISO 180/1A
-40°C	< 10	< 10	kJ/m ²	ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				
				ISO 180/1U
-30°C	75	85	kJ/m ²	ISO 180/1U
23°C	100 kJ/m ²	No Break		ISO 180/1U
Multi-Axial Instrumented Impact Energy				
				ISO 6603-2
-30°C	3.00	--	J	ISO 6603-2
23°C	20.0	65.0	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				
				ISO 6603-2
-30°C	728	--	N	ISO 6603-2
23°C	3030	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	190	--	°C	ISO 75-2/B
1.8 MPa, not annealed	90.0	--	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	--	°C	ISO 306/B50, ISO 306/B120
Melting Temperature ⁸	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				
				ISO 11359-2
Flow: 23 to 55°C	6.0E-5	--	cm/cm/°C	ISO 11359-2

Lateral: 23 to 55°C	7.0E-5	--	cm/cm/°C	ISO 11359-2
Flammability	Dry	Conditioned	Unit	Test Method
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	270 - 290		°C	
Mold Temperature	80.0 - 120		°C	
NOTE				

- | | |
|----|-------------------------------|
| 1. | 150x105x3mm, 80°C MT, 500 bar |
| 2. | 150x105x3mm |
| 3. | 150x105x3mm, 80°C MT, 500 bar |
| 4. | 150x105x3mm |
| 5. | 2.0 mm/min |
| 6. | 2.0 mm/min |
| 7. | 2 mm/min |
| 8. | 10°C/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

