

EMAREX® 400 GF33

Polyamide 66

MRC Polymers, Inc.

Message:

EMAREX® 400 GF33 is a Polyamide 66 (Nylon 66) material filled with 33% glass fiber. It is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30	%	ASTM D955
Water Absorption (Equilibrium)	1.0	%	ASTM D570
Relative Viscosity	50	mPa · s	ASTM D789
Reinforcement Content	30 to 36	%	ASTM D2584
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	101		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	145	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	8270	MPa	ASTM D790
Flexural Strength	214	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	244	°C	
1.8 MPa, Unannealed	232	°C	
Melting Temperature	265	°C	ASTM D789

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT