

# Boda BDF-KK2652

Fluoroelastomer

Chenguang Fluoro & Silicone Elastomers Co., Ltd.

Message:

Material Type: Brown color fluoroelastomer compound, hardness Shore A 60-70.  
Based on bisphenol curable copolymers.  
Features: Excellent mold flow, improved tear resistance and bonding adhesion  
Process Methods: Suitable for compression, transfer, injection and extrusion molding processes.  
Applications: Hoses and rubber strips and low hardness oil seals.  
Lab Testing Curing Condition:  
Press Curing: 10min@170°C.  
Oven: (8+16)hrs@230°C

General Information			
Features	Bondability		
	Good Adhesion		
	Good Flow		
	Good Moldability		
	Good Tear Strength		
	Low Hardness		
Uses	Hose		
	Seals		
Appearance	Brown		
Processing Method	Compression Molding		
	Extrusion		
	Injection Molding		
	Resin Transfer Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.92	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	66		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	11.8	MPa	ASTM D412
Tensile Elongation (Break)	280	%	ASTM D412
Compression Set <sup>1</sup> (200°C, 70 hr)	19	%	ASTM D395
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (250°C, 70 hr)	-10	%	ASTM D573
Change in Ultimate Elongation in Air (250°C, 70 hr)	-9.0	%	ASTM D573

Change in Durometer Hardness in Air (250°C, 70 hr)	2.0		ASTM D573
Change in Tensile Strength (23°C, 70 hr, in Reference Fuel C)	-9.0	%	ASTM D471
Change in Ultimate Elongation (23°C, 70 hr, in Reference Fuel C)	-16	%	ASTM D471
Change in Durometer Hardness (23°C, 70 hr, in Reference Fuel C)	-3.0		ASTM D471
Change in Volume (23°C, 70 hr, in Reference Fuel C)	3.0	%	ASTM D471

#### NOTE

1. 6 mm Buttons

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

