

Desmovit® DP R CF10

Thermoplastic Polyurethane Elastomer (Ester/Ether)

geba Kunststoffcompounds GmbH

Message:

With its mechanical properties TPU Desmovit ® DP R CF stands out from the existing glass-fibrereinforced TPU grades. Desmovit ® DP R CF has very good flexural and tensile proper-ties. The tensile strength, depending on the level of reinforcement, lies between 70 and 135 MPa, and for the flexural strength values of up to 5700 MPa have been achieved. Via the combination of its excellent tensile strength and its high impact strength and notched impact strength, the new hi-tech material is relevant for parts which are subject to knocks and blows. It's also worth mentioning that the new plastic only becomes irreparably damaged after a yield strain of 17.5%.

Applications:

With its low density and its mechanical properties, Desmovit ® DP R CF is ideal for the production of protectors as well as protective cases for tablets and smartphones. The material prevents penetration by sharp objects, absorbs impact force and optimally reduces the remaining energy. The use of the hi-tech plastic is conceivable for diverse applications in the field of sports equipment as well as for use in durable housings for various fields of application such in watches, tools and binoculars. This will ensure, for example, that the optical components of the binoculars will not be damaged through shocks and knocks. The carbon fibre reinforced TPU with its sophisticated mechanical values is antistatic after a certain level of reinforcement and lends itself, with these antistatic properties, to use in rollers, wheels and housings where electrostatic charges are to be avoided. It can therefore be considered for use in mining or the chemical sector as well as for industrial gear wheels. Due to the material's heat and cold stability it is also ideal for use in various outdoor applications.

General Information			
Filler / Reinforcement	Carbon Fiber,10% Filler by Weight		
Features	Good Abrasion Resistance		
	Good Tear Strength		
	Good Thermal Stability		
	High Impact Resistance		
	Hydrolysis Resistant		
	Low Density		
Uses	Electrical Housing		
	Industrial Applications		
	Optical Applications		
	Outdoor Applications		
	Rollers		
	Safety Guards		
	Sporting Goods		
	Wheels		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm ³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 23°C)	68		ISO 868

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/200
Yield	73.0	MPa	
--	73.0	MPa	
10% Strain	64.0	MPa	
Tensile Strain			ISO 527-2/200
Yield	18	%	
Break	20	%	
Flexural Modulus ¹	1700	MPa	ISO 178
Flexural Stress ²	55.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	9.0	kJ/m ²	
23°C	49	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	55	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	119	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time - Dry Air Dryer	4.0 to 6.0	hr	
Processing (Melt) Temp	190 to 210	°C	
Mold Temperature	40.0	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	200 to 220	°C	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT