

SCHULAMID® 6 GF 30

Polyamide 6
A. Schulman Europe

Message:
30% glass fiber reinforced Polyamide 6

General Information				
UL YellowCard		E344659-100854525	E86615-252155	E188844-102210956
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Features		Good Toughness		
		High Stiffness		
		Oil Resistant		
UL File Number		E86615		
Processing Method		Injection Molding		
Resin ID (ISO 1043)		PA6-GF30		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.35	--	g/cm ³	ISO 1183/A
Viscosity Number	145	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	8800	5000	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	160	100	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.5	8.0	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	9.0	--	kJ/m ²	
23°C	14	30	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	--	kJ/m ²	
23°C	85 kJ/m ²	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	215	--	°C	ISO 75-2/Bf
1.8 MPa, Unannealed	200	--	°C	ISO 75-2/Af
Vicat Softening Temperature	210	--	°C	ISO 306/B50
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate	< 100	--	mm/min	ISO 3795

Flammability Classification				IEC 60695-11-10, -20
1.50 mm	HB	--		
3.00 mm	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
1.50 mm	--	650	°C	
3.00 mm	--	650	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

