

Hylac® GP29

Acrylonitrile Butadiene Styrene

Ravago Manufacturing Americas, LLC

Message:

ABS, General Purpose, High Impact

General Information			
Features	General Purpose High Impact Resistance		
Uses	General Purpose		
RoHS Compliance	RoHS Compliant		
UL File Number	E157012		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.03	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238
230°C/10.0 kg	7.3	g/10 min	
230°C/3.8 kg	2.0	g/10 min	
Molding Shrinkage - Flow (3.18 mm)	0.30 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	30.0	MPa	ISO 527-2
Tensile Strain (Break)	10	%	ISO 527-2
Flexural Modulus	1900	MPa	ISO 178
Flexural Stress	50.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	35	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	90.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	83.0	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

