

RTP 4607 HI

Syndiotactic Polystyrene

RTP Company

Message:

Glass Fiber - Impact Modified

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Additive	Impact Modifier		
Features	Impact Modified		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.20	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.010	%	ASTM D570
Moisture Content	0.020	%	
Primary Additive	40	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10300	MPa	ASTM D638
Tensile Strength	121	MPa	ASTM D638
Tensile Elongation (Yield)	1.9	%	ASTM D638
Flexural Modulus	10300	MPa	ASTM D790
Flexural Strength	186	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	150	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	590	J/m	ASTM D4812
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	2.0	hr	
Dew Point	-28.9	°C	
Processing (Melt) Temp	293 to 327	°C	
Mold Temperature	71.1 to 149	°C	
Injection Pressure	68.9 to 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

